

# TECHNICAL SPECIFICATION

Lithium Thionyl Chloride Battery

Model: ER26500M

Established date: 5th July 2022

	Position	Signature	Date
Draft	Product Engineer		
Checked	Technical Manager		
Approved	Chief Engineer		

WUHAN FANSO TECHNOLOGY CO.,LTD.

Floor 2, Building 3, Jiahua Technology Industrial Park, No. 270, Huangjinkou Three Village, Hanyang District, Wuhan City, China

Postal Code: 434000 Tel: 86 27 84452919

---

## Version Record

Version	Reviser	Established Date	Version	Revise page	Revised reason
0	Liu Shao Ping	5th July 2022	A/0	all	Release

## 1. Scope

The document applies to ER26500M battery supplied by WUHAN FANSO TECHNOLOGY CO.,LTD. Specify quality, test method, performance, quality assurance and matters need attention.

## 2. Battery type

Lithium Thionyl Chloride-Spiral type

## 3. Battery system characteristics

Table 1 General characteristics

No.	Item	Characteristic	Remarks
1	Nominal Voltage	3.6V	
2	Nominal Capacity	6000mAh	23±3°C,10mA,2.0V cut off
3	Max. constant current	1000mA	
4	Max. pulse discharge current	2000mA	
5	Operate temperature	-55~80°C	Operation under higher temperature than ambient temperature may lead to reduced capacity and lower voltage reading at the beginning of pulses. If continuous high temperature over +40°C or low temperature down to -20°C usage conditions, please consult FANSO.
6	Dimension	/	See Product Fig
7	Weight	About 57g	
8	Annual self-discharge rate	≤2%	At 23±3°C and humidity 65±10% RH long time storage

## 4. Appearance and structure

#### 4.1 Appearance

Cell appearance, no scratch, swelling, deformation, corrosion, electrolyte leakage and other defects.

#### 4.2 Mark and label

##### 4.2.1 Mark

The battery label contains the following: model, type, company name, voltage, positive and negative mark, safety warning content, certification mark, no littering sign.

##### 4.2.2 Manufacture date

MM/YY print on battery sleeve.

eg: MM/YY: MM-month, YY- year.

#### 5. Typical electrical performances

Table 2

Item	Test condition	Initial Values
Open Circuit Voltage	25±3°C, by three and half digital meter	≥3.64V
Capacity 1	25±3°C, 550mA/6Ω, 2.0V cut off, anode upward	4500mAh/8.2h
Capacity 2	25±3°C, 100mA/33Ω, 2.0V cut off, anode upward	5000mAh/50h
Load voltage	25±3°C, 15Ω, 10seconds, by three and half digital meter	≥3.20V

#### 6. Inspection items, order, sampling method and capacity judgment basis

## 6.1 Incoming inspection

As for the customer's incoming inspection, FANSO recommended sampling according to GB2828.1-2012 standard.

Table 3 Acceptability quality level

No	Item	Technical request	Check level	AQL
1	Dimension	2-6	S-2	0.65
2	Appearance	2-8	II	1.0
3	Open circuit voltage	3-1	II	0.4
4	Load voltage	3-1	II	0.4

Table 4 Sampling amount

Lot size	Sampling amount
$\leq 3200$	32
3200~10000	50
$> 10000$	80

Note: Unless other specified, the above items should be tested within 45 days since receipt of the battery.

## 6.2 Capacity judgment

6.2.1 If the average capacity is not less than the standard value specified in Table 2, and no battery below 90% of the value, the battery capacity is qualified.

6.2.2 If the average capacity is lower than the standard value specified in Table 2, and some battery below 90% of the value, do re-sample test, If the average capacity is not less than the standard value specified in Table 2, and no battery below 90% of the value, the battery capacity is qualified.

6.2.3 if the average capacity is lower than the standard value specified in Table 2 and some battery below 90% of the value during the second test, the battery capacity is unqualified.

## **7. Safety terms**

7.1 Before use, do not remove the battery from the original packaging.

7.2 Do not scattered placed the battery together in order to avoid accidental short circuit.

7.3 Do not heat the battery above 85°C or incinerated.

7.4 Do not recharge the battery.

7.5 Do not mixed with different brand, model or type batteries.

7.6 Do not mix the new and used batteries.

7.7 Do not disassembly or open battery.

7.8 Do not short circuit the battery or reversely contact the positive and negative terminals.

7.9 Do not solder on the battery surface.

7.10 Do not test environment and safety under extrusion without any protection.

7.11 Do not use or store batteries under wet conditions without protection.

7.12 Batteries are not allowed to be used excessively in the equipment without setting the cut-off voltage. After reaching the cut-off voltage, it should be removed from the equipment immediately to stop working.

7.13 Stop using if the battery is found to have heat, odor, discoloration, deformation, or other

abnormalities during using or storage.

7.14 Batteries used should be handled in accordance with local environmental regulations and buried deep underground or into brine.

7.15 If the liquid is splashed on the skin, eyes and clothes, rinse immediately with plenty of water, and then seek medical care immediately.

## **8. Storage**

8.1 Batteries should be used and stored away from static electricity

8.2 Batteries shall be stored not exceeding 30 DEG C and relative humidity of 45% - 75%.

8.3 Keep the battery away from the heat source, away from corrosive gas, avoid direct sunlight, and make sure the storage area is clean, cool, dry and ventilated.

8.4 The battery packing carton height shall not exceed 1.5 meters, and the wooden box shall not exceed 3 meters.

8.5 Batteries should keep the original storage state when not using, after removing the packaging, the battery should not be piled up irregularly.

## **9. Transportation**

9.1 Battery meets the tests and criteria requirements of UN Manual, Part III, subsection 38.3.

9.2 Batteries should be protected against sunlight, fire, rain, immersion, and corrosive substances in transportation.

9.3 Handling and loading should be with care.

9.4 For long transportation, such as shipping, should be kept away from the engine. And in summer should not be prolonged in an airless environment.

## **10. Effective**

10.1 Because the voltage passivation is the basic feature of lithium thionyl chloride battery, if the batteries will not install within 3 months, we suggest to activate the battery before using. please consult the FANSO for activation scheme.

10.2 In practical applications, customer should be responsible for the compatibility and reliability of the battery and the device.

10.3 In any of the following circumstances, FANSO will not take any responsibility: the client' s fails of appropriate treatment, operation, installation, testing, maintenance and inspection of the battery, or do not follow the instructions provided in the specification, notes, terms, and other FANSO instructions.

10.4 This specification is accepted after 6 months from the date of issues if not be refunded.

## **11. Statement**

If you have any questions on the product specifications, please contact with Wuhan Fanso Technology Co. ltd. Fanso reserves the right to amend the product specification.

## **12. Battery dimension**

Please check the specific finished product drawing